



NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE



NC/QC/PD/MW-01/2018-19/OS-CB1A

Date: 21-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-I) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₂₀

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	24-03-18	21-04-18	28	22500	500	22.22	22.89
	002	"	"	"	"	525	23.33	
	003	"	"	"	"	520	23.11	

*As Furnished by Client.

The Results relate only to the items tested.

K. R.
KIRAN. R
M.E, (Civil-Engg)

Page No. 1/1,
Asst. Executive Engineer
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike

For Newzen Consultants Bangalore

Proprietor



NC/QC/PD/MW-01/2018-19/OS-CB2A

Date: 23-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-1) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₂₀

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	26-03-18	23-04-18	28	22500	510	22.67	22.74
	002	"	"	"	"	520	23.11	
	003	"	"	"	"	505	22.44	

*As Furnished by Client.

The Results relate only to the items tested.

K. R.
KIRAN. R
M.E, (Civil-Engg)

Page No. 1/1,

[Signature]
Asst. Executive Engineer
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike

For Newzen Consultants Bangalore
[Signature]
Proprietor



Date: 24-04-2018

NC/QC/PD/MW-01/2018-19/OS-CB3A

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-1) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₂₀

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	27-03-18	24-04-18	28	22500	520	23.11	23.19
	002	"	"	"	"	530	23.56	
	003	"	"	"	"	515	22.89	

*As Furnished by Client.

The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

Asst. Executive Engineer
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike

Page No. 1/1,

For Newzen Consultants Bangalore

Proprietor



NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE



NC/QC/PD/MW-01/2018-19/OS-CB4

Date: 04-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-I) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₁₅

TABLE I.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
I	001	28-03-18	04-04-18	07	22500	300	13.33	13.41
	002	"	"	"	"	310	13.78	
	003	"	"	"	"	295	13.11	

*As Furnished by Client.

The Results relate only to the items tested.

K. R.
KIRAN. R
M.E. (Civil-Engg)

Page No. 1/1,


Asst. Executive Engineer
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike

For Newzen Consultants Bangalore


Proprietor



NC/QC/PD/MW-01/2018-19/OS-CB5

Date: 05-04-2018

I. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-1) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

**RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE
CUBE SPECIMENS**

Dimensions of Specimen : 150 X 150 X 150mm


Grade of Concrete* : M₁₅**TABLE I.1:**

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	29-03-18	05-04-18	07	22500	290	12.89	13.26
	002	"	"	"	"	305	13.56	
	003	"	"	"	"	300	13.33	


*As Furnished by Client.

The Results relate only to the items tested.


Asst. Executive Engineer
Project Sub Division-I
Dasarahalli Zone
Bruhat Bengaluru Mahanagara Palike
Page No. 1/1,


KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore


Proprietor



NC/QC/PD/MW-01/2018-19/OS-CB4A

Date: 25-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-1) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₁₅

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	28-03-18	25-04-18	28	22500	385	17.11	17.48
	002	"	"	"	"	400	17.78	
	003	"	"	"	"	395	17.56	

*As Furnished by Client.

The Results relate only to the items tested.

Asst. Executive Engineer No. 1/1,
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor



NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE



NC/QC/PD/MW-01/2018-19/OS-CB5A

Date: 26-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of Out Door Stadium (Phase-1) Sy No.33 in Ward No.13.}

Ref.: Material testing/PMC/17-18,

Report Required for: Assistant Executive Engineer,
Project Division, Dasarahalli Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Technical Manager, KRIDL.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M₁₅


TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm ²	Maximum Load in K.N	Compressive Strength (N/ mm ²)	Avg. Value
1	001	29-03-18	26-04-18	28	22500	390	17.33	17.26
	002	"	"	"	"	395	17.56	
	003	"	"	"	"	380	16.89	

*As Furnished by Client.

The Results relate only to the items tested.


Asst. Executive Engineer No. 1/1,
Project Sub Division-I
Dasarahalli Zone,
Bruhat Bengaluru Mahanagara Palike


KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore


Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI
NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231,
080 23240187 EMAIL:newzen576@gmail.com